

US-800 & US-900

Revision: 01/07/2016

Page 1 from 2

Uniseal MDF Contact Adhesive

1 – DESCRIPTION

An adhesive set which consists of high viscosity cyanoacrylate adhesive and activator.

2 – PROPERTIES

- High bonding strength.
- Suitable for use on vertical surfaces as it will not drip or slump.
- It is particularly suited to bonding difficult substrates which have a porous or uneven nature since it increases bonding strength by preventing the adhesive to be absorbed by the surface.

3–APPLICATIONS

- It is suitable for the bonding of a very wide range of materials, including acidic surfaces and some porous ones, where rapid bonding times are required.
- Suitable for MDF, wood, chip wood, rubber, most plastics, leather and other common substrates.
- Especially suitable for the applications where cure speed needs to be accelerated.
- Although Uniseal MDF Contact Adhesive has a degree of gap filling ability, it is generally recommended for use on close-fitting parts and fairly smooth, even surfaces.

4 –INSTRUCTIONS

Substrates need to be smooth and have a perfect connection area. Apply a drop on one of the substrates. Join substrates and press firmly for one minute. Application temperature is between +5°C and +35°C.

5–PACKAGING

Product	Volume/Weight	Package
Activator & Glue	200 ml + 40 gr	25
Activator & Glue	200 ml + 45 gr	25
Activator & Glue	200 ml + 50 gr	25
Activator & Glue	400 ml + 80 gr	25
Activator & Glue	400 ml + 100 gr	25

6–STORAGE AND SHELF LIFE

12 months in unopened packaging in a dry and cool storage place at temperatures between +5°C and +25°C.

7-SAFETY

- Cyanoacrylates should ideally be stored in original sealed containers until used.
- Avoid exposure to strong light and heat sources
- Cyanoacrylates can bond to skin within seconds
- Do not drip into skin or into eyes - can cause serious injury to your eyes.
- Will become hard in container if not closed properly!
- Activator is flammable. Do not throw into fire. Do not inhale.
- Activator box is pressured. Do not crush or drill.

8-TECHNICAL PROPERTIES**Glue**

Basis	: Ethyl Cyanoacrylate	
Appearance	: Liquid gel	
Color	: Colorless	
Application Temperature	: +5°C to +35°C	
Density	: 1.06 ± 0.01 gr/cm ³	ASTM D1875
Flashpoint	: > 81 ° C	
Viscosity	: 1200 - 1800 Cps at 25°C	ASTM D1084
Temperature Resistance	: -20°C to +70 °C	

Activator

Basis	: Hexane	
Appearance	: Aerosol	
Color	: Colorless	
Application Temperature	: +5°C to +35°C	
Temperature Resistance	: -20°C to +70 °C	